

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 358 935 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
05.11.2003 Bulletin 2003/45

(51) Int Cl.7: **B01J 23/89**, C07C 209/14,
C07C 209/36, C07C 209/48.

(21) Application number: **03008826.4**

(22) Date of filing: **24.04.2003**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR
Designated Extension States:
AL LT LV MK

(30) Priority: **01.05.2002 US 137053**

(71) Applicant: **AIR PRODUCTS AND CHEMICALS,**
INC.
Allentown, PA 18195-1501 (US)

(72) Inventor: **Ding, Hao**
Macungie, PA 18062 (US)

(74) Representative: **Schwabe - Sandmair - Marx**
Stuntzstrasse 16
81677 München (DE)

(54) **Metal modified Pd/Ni catalysts**

(57) This invention relates to improved catalytic compositions suited for use in hydrogenation processes and to an improved process for hydrogenating organic compounds as in amination of alcohols or hydrogenation of nitro groups to the amine using the catalyst. The catalytic composition is more particularly an improve-

ment in nickel catalysts promoted with palladium carried on a support. The improvement resides in including a promoting effect of a metal M and/or its oxide, selected from Zn, Cd, Cu, and Ag, typically from about 0.01 to 10% by weight of the support.

Description

BACKGROUND OF THE INVENTION

[0001] Processes for the hydrogenation of organic compounds including those having functional groups have been widely practiced. Amination of alcohols, hydrogenation of nitriles to amines, hydrogenation of nitro groups as in the conversion of nitroaromatics to aromatic amines are commonplace industrial reactions. Catalysts used for the industrial hydrogenation of these compounds typically are based upon Group VIII metals. However, cobalt and nickel often are the primary metals employed. Promoter metals have been added to these catalytic metals to alter reactivity, byproduct formation and the like.

[0002] Representative patents and articles illustrating hydrogenation processes and the catalytic metals used therefor are as follows:

[0003] U.S. 3,127,356 discloses an improved process for preparing catalysts for the hydrogenation of organic compounds such as organic nitro compounds. Platinum, palladium or nickel is deposited on an inert support, and then, an oleophilic carbon is added to the system. Subsequently the metal is reduced to an activated state. Activating components, e.g., oxides of iron, nickel magnesium, manganese, chromium, vanadium, and tungsten may be added at various stages.

[0004] U.S. 4,792,626 discloses a process for the hydrogenation of dinitrotoluene to toluenediamine in the presence of a modified Raney nickel catalyst. The Raney catalyst is the product of an alkali treatment of an alloy of from 50-95 wt% aluminum and 4-45 wt% nickel or cobalt. These metals are modified with metals from the 1st, 4th, 5th, 6th, 7th and 8th subgroups of the periodic table. Iron, ruthenium, chromium, molybdenum, tungsten, niobium, tantalum, vanadium, titanium, copper, zirconium and hafnium are preferred. A small proportion of carbon monoxide is added to the reaction to prevent formation of N-alkyl toluenediamine.

[0005] Boccuzzi, F., Guglielminotti, E; Pinna, F., Signoretto, M.; *Surface Composition of Pd-Fe Catalysts supported on Silica*, J. Chem. Soc., Faraday Trans. (1995), 91 (18), 3237-44, disclose the formation of highly dispersed Pd-Fe bimetallic aggregates as catalysts for hydrogenation reactions.

[0006] U.S. 3,935,264 discloses the hydrogenation of dinitrotoluene (DNT) to toluenediamine (TDA) in the presence of an aliphatic alcohol. Preferred catalytic metals include nickel, platinum, palladium and mixtures. Raney nickel is the preferred catalytic metal. Carbon monoxide addition is found to be effective in minimizing the formation of N-alkyl toluenediamine type byproducts in the catalytic hydrogenation of DNT.

[0007] U.S. 6,005,143 discloses the hydrogenation of dinitrotoluene in a monolith catalytic reactor. The catalytic metal employed in the monolith catalytic reactor is a Pd/Ni bimetallic. In these catalysts, the metal loading is about 10% nickel and 1% palladium.

[0008] U.S. 4,743,577 discloses metallic catalysts for hydrogenation and decarbonylation reactions. The catalytic metals are based upon a porous, sintered support and a catalytic metal. Catalytic metals are dispersed upon the support in thin layers or electroplated from a salt solution. Catalyst metals are selected from among palladium, nickel, rhodium, platinum, copper, ruthenium, cobalt and mixtures.

[0009] U.S. 5,296,631 discloses a process for producing N-alkyl-N-methyl amines wherein a higher alcohol is reacted with methylamine. The catalyst employed is either one comprised of copper, zinc and ruthenium or one comprised of copper, zinc and palladium.

[0010] JP S47-91069 discloses the liquid phase hydrogenation of nitriles to amines using a catalyst comprised of nickel and palladium carried on an alumina support. Pd/Ni ratios range from about 0.1 to about 0.8. The proportion of primary amine is related to the level of palladium in the catalyst.

[0011] JP HEI 11-47597 discloses a hydrogenation catalyst employing a porous lithium aluminate possessing spinel as a support. A wide range of catalytic metals are suggested which include ruthenium, rhodium, silver, palladium carried on the support. Divalent metals such as magnesium zinc, cobalt nickel and copper are suggested as an additive.

[0012] Some of the problems associated with prior art palladium promoted nickel hydrogenation catalysts, i.e., Pd/Ni bimetallic catalysts, include that of relatively low selectivity and deactivation. Deactivation can be caused by a sintering of the metal and/or fouling caused by undesirable byproduct formation. Ring hydrogenated products (lights) and oligomer products (heavies) are believed to be the common byproducts causing fouling of the catalysts.

BRIEF SUMMARY OF THE INVENTION

[0013] This invention relates to improved catalytic compositions suited for use in hydrogenation processes and to an improved process for hydrogenating organic compounds as in amination of alcohols or hydrogenation of nitro groups to the amine using the catalyst. The catalytic composition is more particularly an improvement in palladium/nickel catalysts which are carried on a support. The improvement resides in including a promoting effective amount of a metal M selected from Zn, Cd, Cu, and Ag, typically from about 0.01 to 10% by weight of the support.

[0014] Significant advantages may be achieved by the use of the catalytic compositions in hydrogenation processes and these include:

- an ability to achieve high selectivity of desired product;
- an ability to achieve excellent rates of reaction during hydrogenation; and,
- an ability to achieve excellent catalyst life partially due to minimal byproduct formation.

DETAILED DESCRIPTION OF THE INVENTION

[0015] As illustrated in the Background of the Invention, Pd/Ni as bimetallics are known and widely used as catalysts for a number of hydrogenation reactions, such as the hydrogenation of nitroaromatic compounds to aromatic amines. The hydrogenation of dinitrotoluene (DNT) to toluenediamine (TDA) and the hydrogenation of nitriles are representative.

[0016] These catalytic metals are carried on a support, whether active or not, such as alumina or silica. Other materials that may be used as supports include titania, lithium aluminate, zeolites, kieselguhr, diatomaceous earth, carbon and so forth. Monolith substrates having from 100 to 1200 cells per inch, preferably from 400 to 800 cells per inch may be used in an embodiment of the invention. Monolith substrates may be made from carbon, cordierite, ceramics and numerous other components. Such substrates may be used to anchor the above mentioned support materials for fixed bed applications.

[0017] The active metals, i.e., Ni and Pd, for effecting the hydrogenation reactions are impregnated into or on the support by conventional methods such as incipient wetness or other methods of impregnation and deposition. In the case of monolithic catalysts, washcoat support materials, such as alumina, lithium aluminate and the like, are added to the surface of monolith substrate as catalyst support. The active metals are added and subsequently fixed to the washcoat support to form a catalyst. Typically the metals are applied to or incorporated into the support material using the metal oxides which subsequently get reduced to the active metal.

[0018] The active metals are incorporated into the support, e.g., by impregnation in various amounts. The level of nickel, as metal, incorporated into the support will range from about 10 to 25 wt%, preferably from 15 to 20 wt%; the palladium in the support will range from about 0.01 to 20 wt%, preferably from 0.5 to 1.5 wt%, and the amount of promoting metal M in the support will range from about 0.001 to 10 wt%, preferably from 0.1 to 2 wt%. Typically, the weight ratio of nickel to palladium will range from 1-100:1, preferably from 10-40:1 and the weight ratio of nickel to promoting metal M will range from about 10-1000:1, preferably from 10-200:1 and the weight ratio of palladium to metal M will range from 0.5-10:1.

[0019] The catalysts described herein are well suited for hydrogenation reactions associated with the catalytic hydrogenation of organic compounds employing palladium/nickel catalysts. Hydrogenation reactions that can be carried out using the improved catalysts include the hydrogenation of unsaturated hydrocarbons, amination of alcohols, conversion of nitro groups to amines and the hydrogenation of nitriles. Unsaturated hydrocarbons which may be hydrogenated are aromatic compounds, olefins and alkynes.

[0020] Examples of alkanols suited for amination by reaction with ammonia in the presence of hydrogen include lower C₁₋₈ alkanols, such as methanol, ethanol, *i* and *n*-propanol, butanol, and so forth, and cycloaliphatic alcohols, such as cyclohexanol. Nitriles which can be hydrogenated include the C₁₋₈ aliphatic nitriles, e.g., acetonitrile, propionitrile, butyronitrile, acrylonitrile and so forth. One of the important industrial applications for these catalysts is the hydrogenation of aromatic nitro compounds to form the aromatic amines. Examples include the hydrogenation of mononitrotoluene and dinitrotoluene (DNT).

[0021] Although not intending to be bound by theory, in the case of DNT hydrogenation, the presence of Pd keeps Ni at a reduced state at effective DNT conversion temperatures. Therefore, such catalysts provide good DNT hydrogenation activity to TDA. However, Pd is also active in ring hydrogenation, causing the formation of light byproducts (lights) in the process. The metals M tend to reduce the lights and byproducts formed in the hydrogenation process.

Example 1

[0022] Modification Of Pd/Ni Bimetallic Monolith Catalyst With Zinc -- Five zinc modified Pd/Ni impregnated monolith catalysts were prepared as follows. A commercial Pd/Ni monolith catalyst comprised of a cordierite monolith substrate that contained 20 wt% of alumina washcoat support having Pd in an amount of 1.0 wt% with respect to the washcoat support and Ni in an amount of 20.0 wt% with respect to the washcoat support was dipped into an aqueous solution containing 2 wt% Zn(NO₃)₂(6H₂O) at room temperature. The resulting wet monolith catalyst was dried at 110°C for 4 hours and then calcined at 380°C for 6 hours. Different Zn loadings were achieved by changing the concentration of Zn(NO₃)₂(6H₂O) in the dipping solution from 0.2 wt% to 20 wt%. Zn loadings in the five monolith catalysts resulting from zinc addition were 0.29%, 0.48%, 0.80%, 3.0%, 4.8% with respect to the weight of the washcoat support. Zinc

EP 1 358 935 A1

levels were determined by Inductive Coupled Plasma (ICP).

Example 2

[0023] Modification Of Pd/Ni Bimetallic Monolith Catalyst With Copper -- The procedure of Example 1 was followed except that copper modification was achieved by utilizing a 2 wt% $\text{Cu}(\text{NO}_3)_2$ solution. 1.0% Cu with respect to the weight of the washcoat support was added.

Example 3

[0024] Modification Of Pd/Ni Bimetallic Monolith Catalyst With Silver -- Silver modification was achieved with 2 wt% AgNO_3 solution using the method described in Example 1. 1.0% Ag with respect to the weight of the washcoat support was added.

Example 4

[0025] Influence Of Zn Concentration On DNT Hydrogenation Selectivity -- The effectiveness of the five zinc modified Pd/Ni monolith catalysts prepared in Example 1 for performance and selectivity control in the hydrogenation of dinitrotoluene (DNT) was determined using a batch reactor.

[0026] A toluenediamine/water (TDA/water) heel was first charged to the batch reactor and the monolith catalyst placed in the reactor. The mixture was brought to reaction conditions (140°C, 600 psi H_2). DNT was then pumped in at four different rates (1, 2, 4, 8 g/min) for a total duration of 1 hour. The activity of the catalyst (hydrogenation rate) was recorded during this period of time. The DNT feeding was stopped after 1 hour and the TDA product mixture was kept at reaction conditions for additional 2 days, during which the selectivity of the catalyst was checked by GC through periodical sampling the reactor.

[0027] It was found that the presence of Zn in the Pd/Ni monolith catalyst effectively suppressed formation of lights and tars (byproducts) even at concentrations as low as 0.3 wt% based on support. As a generalized trend, a higher concentration of Zn in the monolith catalyst gave even better selectivity control up to around 0.8 wt%. Then the control leveled off with virtually no lights formation, and yet the activity of the catalyst was not compromised even at high Zn loading of 5 wt%. Table 1 presents data showing the DNT hydrogenation selectivity enhancement by the Zn modified catalysts.

Table 1

Zn%	Lights%	Tars%
0.00	7.50	1.00
0.29	2.90	2.30
0.48	2.20	1.00
0.80	0.30	0.10
3.00	0.29	0.44
4.80	0.19	0.54

Example 5

[0028] Influence Of Different Metal Promoters On DNT Hydrogenation Selectivity -- The procedure of Example 4 was followed to determine the effectiveness of the Cu and Ag modified monolith catalysts formed in Examples 2 and 3. The amounts of light products generated with each modified catalyst were compared against the unmodified Pd/Ni catalyst. Table 2 shows the effect of metal promoters on light products formation. The data in Table 2 demonstrates that Cu and Ag were effective promoters to suppress the formation of light products in the DNT hydrogenation process. However, their effectiveness was less than that of zinc as illustrated in Table 2.

Table 2

	Lites%	Tar%
Pd/Ni	7.50	1.00

Table 2 (continued)

	Lites%	Tar%
Pd/Ni/Zn	0.30	0.10
Pd/Ni/Cu	1.50	1.10
Pd/Ni/Ag	2.00	2.30

[0029] In summary, a Zn modified Pd/Ni catalyst resulted in overall lights formation of 0.3% in 48h (total byproduct: <1%). This high level of selectivity was unexpected as the unmodified catalyst typically resulted in 7.5% lights (total byproduct: 9%) under the same conditions (140°C, 600 psi H₂). The Cu and Ag catalysts are also significantly better than the non-modified Pd/Ni catalyst but not as good or as effective in promoting selectivity as zinc.

Example 6

[0030] Synthesis Of Ni(20%)/Pd(1%)/Zn(1%) On Alumina Support -- An alumina supported catalyst containing palladium, nickel and zinc was prepared as follows. Initially 1.8g zinc nitrate hexahydrate was dissolved in approximately 4 ml HPLC grade H₂O and then 39.6g nickel nitrate hexahydrate and 5 ml HPLC grade water were added to the zinc solution. The mixture was stirred on a hotplate. When completely dissolved, 4.9g palladium nitrate solution (8.2%Pd) was added to the zinc/nickel solution. 31.2g gamma alumina (heat treated Catalpal® B alumina) was then blended in until alumina was uniform in color. The mixture was transferred to a porcelain dish, dried at 110°C in air for 1 hr and further calcined at 380°C in air for 4 hrs.

Example 7

[0031] Hydrogenation Of Butyronitrile Using Ni(20%)/Pd(1%)/Zn(1%) On Alumina Support -- 1.2g of the catalyst of Example 6, was reduced initially by hydrogen at 500°C and added to a 500 ml Parr reactor. Butyronitrile (80g, 98%, Aldrich) was then charged to the reactor. The reactor was brought to a temperature of 125°C and pressurized to 500 psig with H₂. The reactor was stirred at 1500 rpm. The hydrogenation reaction was stopped when hydrogen no longer was consumed. Multiple uses of the same catalyst were achieved by discharging the reaction product through a internal filter and recovering the used catalyst. The used catalyst then was recharged to the reactor and fresh feed added. The final products were analyzed by GC and the results are shown in Table 3.

Table 3

Use	T ₉₅ (min)	Conv (%)	Butylamine (%)	Dibutylamine (%)	Tributylamine (%)
1	196	99.7	69.3	28.7	0.5
2	127	98.3	64.9	28.2	0.7
3	125	99.8	66.2	30.9	0.8
4	122	99.8	67.3	31.6	0.9

[0032] The results show excellent conversion of the nitrile to the primary amine. Minimal amounts of tertiary amine were formed.

Example 8

[0033] Ethanol Amination Using Ni(20%)/Pd(1%)/Zn(1%) On Alumina Support -- A Ni(20%)/Pd(1%)/Zn(1%) catalyst as prepared in Example 6 was first pressed into pellets and then screened for particle size using 12 and 18 mesh screens. Approximately 10cc of catalyst was weighed out and placed in a tube reactor. The temperature of the reactor was slowly increased to 410°C over a 2-hour period. To reduce the catalyst metal, the catalyst was kept at this temperature under 100 psi hydrogen with a flow rate of 80 ml/min for 4 hours. Once the catalyst metal was reduced, the temperature was lowered to 185°C and ethanol (7.0 ml/hr) was fed to the reactor along with ammonia and hydrogen (NH₃/ethanol/H₂ = 2/1/1.5 molar ratio). The sample stream was analyzed by GC equipped with a FID detector. The data is shown in Table 4.

Table 4

Time on Stream	EtOH Conv. (%)	MEA (%)	DEA (%)	TEA (%)
24hr	84.602	34.551	47.421	18.028
48 hr	83.550	34.635	47.716	17.649
72hr	82.587	35.209	47.069	17.722
144hr	82.143	34.479	47.501	18.020
168hr	80.714	35.834	46.669	17.497

[0034] The results show excellent conversion and catalysts life were achieved using the zinc modified Pd/Ni catalyst.

Claims

1. In a palladium/nickel catalytic composition carried on a support which is suited for use in a hydrogenation process, the improvement which resides in the inclusion of a promoting effective amount of a metal M selected from the group consisting of zinc, cadmium, copper, and silver.
2. The catalytic composition of Claim 1 wherein the nickel is present in an amount from about 10 to 25 percent by weight of the support.
3. The catalytic composition of Claim 2 wherein the palladium is present in an amount from 0.01 to 20 percent by weight of the support.
4. The catalytic composition of Claim 3 wherein the metal M is present in an amount from about 0.001 to 10 wt% of the support.
5. The catalytic composition of Claim 4 wherein the weight ratio of nickel to palladium is from 1-100:1.
6. The catalytic composition of Claim 5 wherein the weight ratio of nickel to metal M is from about 10-1000:1.
7. The catalytic composition of Claim 6 wherein the weight ratio of palladium to metal M is from 0.5-10:1.
8. The catalytic composition of Claim 7 wherein the metal M is zinc.
9. The catalytic composition of Claim 8 wherein the support is selected from the group consisting of alumina, lithium aluminate, carbon, silica, titania, zeolite, kieselguhr or cordierite monolith with above supports as washcoat.
10. The catalytic composition of Claim 9 wherein the nickel is present in an amount of from 15 to 20% by weight of the support, the palladium is present in an amount from 0.5 to 1.5% by weight and the zinc is present in an amount from 0.1 to 2% by weight.
11. In a process for the catalytic hydrogenation of organic compounds wherein the organic compound is contacted with hydrogen in the presence of a catalytic amount of a palladium/nickel catalyst, the improvement which comprises employing the catalyst composition of Claim 1.
12. The process of Claim 11 wherein the nickel is present in an amount from 10 to 25 percent by weight of the support.
13. The process of Claim 12 wherein the palladium is present in an amount from 0.01 to 20 percent by weight of the support.
14. The process of Claim 13 wherein the amount of the metal M is present in an amount from about 0.001 to 10 percent of the support.
15. The process of Claim 14 wherein the weight ratio of nickel to palladium is from 1-25:1, the weight ratio of nickel

EP 1 358 935 A1

to metal M is from about 10-200:1 and the weight ratio of palladium to metal M is from 0.5-10:1.

16. The process of Claim 14 wherein the catalyst is present in the monolithic form.

5 17. The process of Claim 16 wherein the organic compound is selected from the group consisting of a nitrile or a nitroaromatic and the nitrile is an aliphatic nitrile having from 1-8 carbon atoms.

18. The process of Claim 17 wherein the nitrile is selected from the group consisting of acetonitrile, propionitrile and butyronitrile.

10 19. The process of Claim 16 wherein the organic compound is a nitroaromatic compound selected from the group consisting of mononitrobenzene and dinitrotoluene.

15 20. The process of Claim 11 wherein the hydrogenation process comprises the amination of an alcohol in the presence of hydrogen.

21. The process of Claim 20 wherein the nickel is present in an amount from 15 to 20 percent by weight of the support

20 22. The process of Claim 21 wherein the palladium is present in an amount from 0.1 to 1.5 percent by weight of the support.

23. The process of Claim 22 wherein the metal M is present in an amount from about 0.1 to 2 percent of the support.

25 24. The process of Claim 23 wherein the weight ratio of nickel to palladium is from 1-25:1, the weight ratio of nickel to metal M is from about 10-200:1 and the weight ratio of palladium to metal M is from 0.5-10:1.

30


35

40

45

50

55





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 03 00 8826

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 238 365 A (ANTOS GEORGE J) 9 December 1980 (1980-12-09) * claims 1,5-7; examples *	1-24	B01J23/89 C07C209/14 C07C209/36 C07C209/48
X	US 4 792 622 A (SAWAMOTO YUZI ET AL) 20 December 1988 (1988-12-20) * claim 1; examples *	1-24	
X	US 3 781 227 A (FOKIN E ET AL) 25 December 1973 (1973-12-25) * claims 1,5; examples *	1-24	
A	US 5 932 769 A (ARMOR JOHN NELSON ET AL) 3 August 1999 (1999-08-03)		
A	US 6 005 143 A (PARRILLO DAVID JOSEPH ET AL) 21 December 1999 (1999-12-21)		
A	EP 1 036 784 A (DEGUSSA) 20 September 2000 (2000-09-20)		
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			B01J C07C
Place of search		Date of completion of the search	Examiner
MUNICH		24 July 2003	Schoofs, B
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 00 8826

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

24-07-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4238365 A	09-12-1980	US 4298462 A	03-11-1981
		US 4374046 A	15-02-1983
US 4792622 A	20-12-1988	JP 1690850 C	27-08-1992
		JP 3054931 B	21-08-1991
		JP 62149648 A	03-07-1987
		DE 3641666 A1	02-07-1987
		ES 2001465 A6	16-05-1988
		FR 2592041 A1	26-06-1987
US 3781227 A	25-12-1973	DE 2100373 A1	07-09-1972
		FR 2122770 A5	01-09-1972
		GB 1343289 A	10-01-1974
US 5932769 A	03-08-1999	NONE	
US 6005143 A	21-12-1999	BR 9903380 A	17-10-2000
		CN 1245163 A	23-02-2000
		DE 69906893 D1	22-05-2003
		EP 0978505 A2	09-02-2000
		JP 2000080061 A	21-03-2000
		KR 2000017021 A	25-03-2000
EP 1036784 A	20-09-2000	DE 19911865 A1	28-09-2000
		BR 0001335 A	25-03-2003
		EP 1036784 A1	20-09-2000
		JP 2000281631 A	10-10-2000